Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

- 1-49. (Cancelled)
- 50. (Currently Amended) An electroluminescent device comprising a A wettability changing layer comprising a wettability changing material, wherein:

 the wettability changing layer has a thickness of 50-100 to 2,000-1,000 angstroms;

the layer is conductive;

the wettability changing layer is capable of charge-injection and/or charge-transfer; and

wettability of the layer changes when light energy is applied to a first portion of the wettability changing layer, a wettability of the first portion changes; and when the wettability of the first portion is changed, a further material can be formed pattern wise on the wettability layer.

- 51. (Cancelled)
- 52. (Currently Amended) The electroluminescent device layer according to claim 50, wherein the wettability changing layer comprises at least further comprising a photocatalyst and a binder.
- 53. (Currently Amended) The electroluminescent device <u>layer</u> according to claim 52, wherein the photocatalyst is titanium dioxide.
- 54. (Currently Amended) The electroluminescent device <u>layer</u> according to <u>elaim</u> 52<u>claim 50</u>, wherein the binder is <u>further comprising a binder comprising an</u> organopolysiloxane obtained by hydrolyzing and polycondensing chlorosilane or alkoxysilane.

- 55. (Currently Amended) The electroluminescent device layer according to elaim 52 claim 50, wherein the further comprising a binder is an organopolysiloxane obtained by crosslinking a reactive silicones silicone.
- 56. (Currently Amended) The electroluminescent device-layer raccording to claim 50, wherein the wettability changing layer comprises further comprising a substance binder that facilitates the injection of a charge or the transfer of a charge comprising fluoroalkyl groups.
 - 57-63. (Cancelled)
- 63. (Currently Amended) The electroluminescent device layer according to elaim 56claim 50, wherein the substance that facilitates the injection of a charge or the transfer of a charge is further comprising a metal salt capable of facilitating charge-injection and/or charge-transfer.
 - 64. (Cancelled)
- 65. (Currently Amended) The electroluminescent device layer according to claim 50, wherein:

 light energy has been applied to the first portion of the wettability changing layer to change the wettability of the first portion; and

 one or more materials have been formed pattern wise on the wettability changing layer in a pattern corresponding to a pattern of wettability formed by applying light energy to the first portion the metal salt selected from the group consisting of FeCl₂, FeCl₃, Cr(NO₃)₃, CrCl₃, NaNO₃, Ca(NO₃)₂, Sr(NO₃)₂, Co(NO₃)₂, CoCl₂, Cd(NO₃)₂, Mg(NO₃)₂, Cu(CH₃COO)₂, Cu(NO₃)₂, Ni(NO₃)₂, Mn(NO₃)₂, MnCl₂, PbNO₃, RuCl₃, IrCl₄, Ir(NO₃)₃, ScCl₃, Sc(NO₃)₃, H₂PtCl₆, RhCl₃, Tb(NO₃)₃, Pr(NO₃)₂, Dy(NO₃)₃, Sm(NO₃)₃, Ga(NO₃)₂, Gb(NO₃)₃, Yb(NO₃)₃, NbCl₅, ZrCl₄, Zr(NO₃)₂, KNO₃, LiNO₃, HAsCl₄, Pd(NO₃)₂, Eu(NO₃)₂, Nd(NO₃)₂, NiCl₃, Ce(NO₃)₃, CsNO₃, Er(NO₃)₃, Ba(NO₃)₂, La(NO₃)₃, AgCl₃

CH₃CH(OH)COOAg, AgNO₃, TINO₃, Y(NO₃)₃, Pb(NO₃)₂, Ho(NO₃)₃, Bi(NO₃)₃ and mixtures thereof.

66-67. (Cancelled)